

## Declaration of Performance

Declaration of Performance in accordance with EU-regulation 305/2011, Annex III

**No. 013CPR2013-07-01**

1. Unique identification code of the product-type:

**Hot rolled structural steel plate S355N / 1.0545**

2. Type, batch or serial number or any other element allowing identification of the construction product as required under Article 11(4):

**Plate S355N according to EN 10025-3**

3. Intended use or uses of the construction product, in accordance with the applicable harmonized technical specification, as foreseen by the manufacturer:

**Welded, bolted and riveted structures**

4. Name, registered trade name or registered trade mark and contact address of the manufacturer as required pursuant Article 11(5):

**NLMK DanSteel A/S**  
**Havnevej 33**  
**DK 3300 Frederiksværk, Denmark**  
**Tel. +4547770333**  
[www.dansteel.dk](http://www.dansteel.dk)

5. Name and contact address of the authorised representative whose mandate covers the tasks specified in Article 12(2):

**Not applicable.**

6. System or systems of assessment and verification of constancy of performance of the construction product as set out in Annex V:

**System 2+**

7. In case of the declaration of performance concerning a construction product covered by a harmonised standard:

**Notified factory production control certification body TÜV Nord Systems GmbH & Co. KG No. 0045 conducted an initial inspection of the plant and of the factory production control and performs continuous monitoring and conformity assessment of the factory production control.**

## 8. Declared performance

Essential characteristic		Performance				Harmonised technical specification
Tolerances on dimensions and shape	Thickness	In accordance with EN 10029: 2011				EN 10025-1 :2004
	Width	In accordance with EN 10029: 2011				
	Length	In accordance with EN 10029: 2011				
Yield Strength	Nominal thickness (mm)		Values ReH (MPa)			
	>	≤	min	max		
		16	355			
	16	40	345			
	40	63	335			
	63	80	325			
	80	100	315			
	100	150	295			
Tensile Strength	Nominal thickness (mm)		Values Rm (MPa)			
	>	≤	Min	max		
	3	100	470	630		
	100	200	450	600		
Elongation	Nominal thickness (mm)		Values A5 (%)			
	>	≤	min	max		
	3	63	22			
Impact Strength	Nominal thickness (mm)		Values (J @ -20°C)			
	>	≤	min	max		
	3	200	40			
Weldability CEV	Nominal thickness (mm)		Values (%)			
	>	≤	min	max		
	3	63		0,43		
	63	200		0,45		
Durability (chemical composition)	Nominal thickness (mm)		Values (%)			
	>	≤	min	max		
	3	200				
				C: 0,20 Si: 0,50 Mn: 0,90-1,65 P: 0,030 S: 0,025 Nb: 0,05 V: 0,12	Ti: 0,05 Cr: 0,30 Ni: 0,50 Mo: 0,10 Cu: 0,55 N: 0,015	

9. The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 8. This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 4. Signed for and on behalf of the manufacturer by:

Zibrandt Greisen  
Chief Metallurgist.